AMENDMENTS TO THE CLAIMS

1. (Currently amended) A method for forming a solder resist pattern comprising the .

steps of:

pre-treating both sides of a double-sided printed circuit board;

laminating a semi-cured thermosetting film on the both sides of the printed circuit board;

and

irradiating a laser beam to the laminated thermosetting film according to a solder resist

mask pattern to selectively remove the thermosetting film, the solder resist mask pattern having

been previously designed prior to irradiating, wherein the laser beam is produced by a laser that

is used to produce via holes in the printed circuit board.

2. (Original) The method for forming a solder resist pattern according to claim 1,

wherein the pretreatment includes scrubbing.

3. (Original) The method for forming a solder resist pattern according to claim 1,

further comprising curing the semi-cured thermosetting film after laminating the thermosetting

film.

4. (Currently amended) A method for forming a solder resist pattern comprising the

steps of:

pre-treating a portion exposed from a plurality of layers constituting a multilayer printed

circuit board fabricated by buildup process;

laminating a thermosetting film on the pretreated portion; and

irradiating a laser beam to the laminated thermosetting film according to a solder resist

mask pattern to selectively remove the thermosetting film, wherein the laser beam is produced by

a laser that is used to produce via holes in the printed circuit board.

LAW OFFICES OF CHRISTENSEN O'CONNOR JOHNSON KINDNESSPLE

1420 Fifth Avenue Suite 2800

Seattle, Washington 98101 206.682.8100

5. (Original) The method for forming a solder resist pattern according to claim 4, wherein the pretreatment includes scrubbing.

6. (Currently amended) The method for forming a solder resist pattern according to claim 5, further comprising curing the semi-cured thermosetting film after laminating the

thermosetting film.

7. (Currently amended) A method for forming a solder resist pattern comprising the

steps of:

pre-treating a portion exposed from a plurality of layers constituting a multilayer printed ·

circuit board fabricated in a parallel manner;

laminating a thermosetting film on the pretreated portion; and

irradiating a laser beam to the laminated thermosetting film according to a solder resist

mask pattern to selectively remove the thermosetting film, wherein the laser beam is produced by

a laser that is used to produce via holes in the printed circuit board.

8. (Original) The method for forming a solder resist pattern according to claim 7,

wherein the pre-treatment includes scrubbing.

9. (Currently amended) The method for forming a solder resist pattern according to

claim 8, further comprising curing the semi-cured thermosetting film after laminating the

thermosetting film.

10. (Previously presented) The method of claim 1, wherein the laser is a yttrium

aluminum garnet laser, excimer laser, or carbon dioxide laser.

11. (Previously presented) The method of claim 4, wherein the laser is a yttrium

aluminum garnet laser, excimer laser, or carbon dioxide laser.

12. (Previously presented) The method of claim 7, wherein the laser is a yttrium

aluminum garnet laser, excimer laser, or carbon dioxide laser.

LAW OFFICES OF CHRISTENSEN O'CONNOR JOHNSON KINDNESS^{PLC} 1420 Fifth Avenue

Suite 2800 Seattle, Washington 98101 206.682.8100

-3-

13. (New) A method for forming a solder resist pattern, comprising:

pre-treating both sides of a double-sided printed circuit board to provide pre-treated sides of a printed circuit board;

applying a semi-cured thermosetting film on the pre-treated sides of the printed circuit board to provide a thermoset film on the printed circuit board; and

irradiating a laser beam on the thermoset film to selectively remove the thermoset film to provide a solder resist pattern.

- 14. (New) The method of claim 13, wherein pre-treating includes scrubbing.
- 15. (New) The method of claim 13, further comprising curing the thermosetting film.
- 16. (New) A method for forming a solder resist pattern comprising:

pre-treating a portion exposed from a plurality of layers, constituting a multi-layer printed circuit board fabricated by a buildup process to provide a pre-treated portion;

laminating a thermosetting film on the pre-treated portion to provide a thermoset film; and

irradiating a laser beam on the thermoset film to selectively remove the film to provide a solder resist pattern.

- 17. (New) The method of claim 16, wherein pre-treating includes scrubbing.
- 18. (New) the method of claim 16, further comprising curing the thermosetting film.
- 19. (New) A method for forming a solder resist pattern, comprising:

pre-treating a portion exposed from a plurality of layers constituting a multi-layer printed circuit board fabricated in a parallel manner to provide a pre-treated portion;

laminating a thermosetting film on the pre-treated portion to provide a thermoset film; and

irradiating a laser beam on the thermoset film to selectively remove the thermoset film to provide a solder resist pattern.

- 20. (New) The method of claim 19, wherein pre-treating includes scrubbing.
- 21. (New) The method of claim 19, further comprising curing the thermosetting film.